

AQUA TS 430

WATERBASED 1K / 2K TOPCOAT



DESCRIPTION

AQUA TS 430 is a clear coat water based for interior wood products that ensures good film hardness, transparency and smoothness to the touch.



PRODUCT DATA

Color	Clear	VOC less exempts	68.26 g/L	0.57 lb/gal
Solids % by Vol	30% ± 2%	VOC actual	106.26 g/L	0.89 lb/gal
Solids %by Wt	35% ± 2%	Photochemical reactive	No	
Density	1.04 ± 0.02	Flash Point (PM/CC)	N/A	
Viscosity 23°C/73°F (Ford #4)	135-145	Shelf life	12 months (at 15-25°C/59-77°F)	
Gloss(On Black glass @60°)	20, 35,50,90/Available in other gloss level	Theo-coverage @1 mil dry	480-500 Sq.Ft/gal	9-10 m ² /L

PREPARATION/APPLICATION

Working Temp	>18°C/65°F surface, coating and air
Catalyzation	Optional for optimal chemical resistance 5 % by volume using CW 7800 or CW 7900 catalyst.
Pot life	2 hours (when catalysed with CW 7800 catalyst)
Reducer	Product can be applied without reduction. If reduction is needed to optimize application, reduce 5-10% by volume with distilled water, or HRX L (medium reducer), or HRX SL (slow reducer) and HRX Retarder can be used to slow AQUAFOND 425
Suggested sealer	AQUAFOND 425
Application	<ul style="list-style-type: none"> Stain- Stain or color wood if desired and allow to dry. Consult your local representative for appropriate stain offering Seal- Apply AQUAFOND 425 at 4.0 – 6.0 wet mils. Air dry thoroughly. Sand with 220-320 grit sandpaper and remove all sanding dust. Topcoat within 8 hours of sanding. .Refer to corresponding data sheet for details Topcoat – apply AQUA TS 430.at 4.0 - 6.0 mils wet. Apply an additional topcoat for greater build <p>Note: Oak or other species of wood rich in tannic acid can discolor. Users are urged to test the system under shop conditions.</p>
Surface Preparation	Wood surface must be dry and finish sanded with 180 grit sandpaper Substrate should be clean and free of grease and oil to ensure optimum adhesion and coating performance properties. Moisture content of the wood should be between 6%-8%.
Use Directions	For interior use only. Catalyze optional, adjust viscosity and stir thoroughly before application to avoid variations application. Dry time can be directly impacted by many factors, including film thickness. Users are urged to test the system under shop conditions.
App equip.	Conventional, Airless and Air Assist Equipment.
Tinting	Can be tinted up to 10% maximum with colorants AQUATINT
Cleanup	Clean tools/equipment immediately after use with HRX Kleener or warm water.

DRYING TIMES

Method	Drying temperature.	Drying Time (@ 50%RH and thickness @ 4 mil WET)			
Air Drying	23°C/74°F	Dust free time	15 minutes	Dry to sand	90 minutes
		Dry to touch	25 minutes		
		Dry to Handle	45 minutes	Dry to stack	24 hours
Force dry	45 °C/110°F	30 minutes			

Note: Dry times are greatly affected by film build, porosity of substrate, air movement as well as heat and humidity. Minimum curing temperatures of 23°C/74°F must be maintained throughout curing cycle to achieve the film integrity as stated in product features.

AQUA TS 430

WATERBASED 1K / 2K TOPCOAT



APPLICATION RECOMMENDATIONS

APPLICATION EQUIPMENT SETTINGS

Method of Application	Air Pressure (PSI)	Fluid Pressure (PSI)	TIP size (mm)	Dilution %	Thickness Film (Mils)
Conventional spray	40-60	-	2-2.5 / 0,078-0.098	5-10	4-6
Air Assist Airless	20-30	1100-1600	9-11 / 0,35-0.43	5-10	4-6

The use of pre-atomizers and pre-heaters, to bring the temperature to 30 – 40 °C, ensures a correct application regardless the room temperature. The drying process should be carried out in environments with adequate air ventilation (the recycle of air in the drying room should be carried out every 15-20 minutes).

Note: All measurements and application equipment settings are based on application at a temperature of 77°F. Viscosity will vary depending on the temperature of the liquid. The above-mentioned application equipment recommendations are guidelines only. The noted settings are starting point recommendations and that adjustment to the settings and equipment may be needed to obtain the desired results. Please refer to your specific equipment manufacturer's recommendations for equipment set-up.

SPECIFICATIONS

- For interior use only.
- Must be agitated before and during using. Avoid vigorous agitation which may cause foaming.
- Use stainless steel spray equipment. Tank, piping, and containers should be lined steel or plastic.
- Very low temperature application (less than 12°C) may cause poor mechanical and chemical film properties.
- Total film thickness must not exceed 4.0 mils dry film because heavier films may show cracking tendencies.
- Excessive wet film thicknesses (>4.0 mils wet) may sag.
- Very low humidity may cause mudcracking and poor film properties.
- When finishing Redwood, Red or White Oak, Pine and Cedar wood with water based finishes, tannins may be extracted from the wood by the water and cause staining and/or discoloration of the stain, sealer, and/or topcoat. This tannin bleed is most evident with white or pickled stains and clear topcoats. Users are urged to thoroughly test the system under shop conditions
- Natural Finished Woods (unstained) will change color on aging and exposure to light. This is a natural phenomenon. Clear finishes will not prevent the wood from changing color.
- Apply over recommended LORCHEM sealer. Please contact your LORCHEM representative for system recommendations.
- Do not expose to freezing temperatures. The liquid coating will not handle any freeze/thaw cycles.

CAUTIONS

TESTING

Due to the wide variety of substrates, surface preparation methods, application methods, and environments, the customer should test the complete system for adhesion, compatibility and performance prior to full scale application.

THESE PRODUCT ARE DESIGNED FOR INDUSTRIAL SHOP APPLICATION AND PROFESSIONAL USE ONLY

Thoroughly review Safety Data Sheet (SDS) for safety information and cautions prior to using this product. Please direct any questions or comments to your local representative.

PDS

Product Data Sheets are periodically updated to reflect new information relating to the product. It is important that the customer obtain the most recent Product Data Sheet for the product being used. The information, rating, and opinions stated here pertain to the material currently offered and represent the results of tests believed to be reliable. However, due to variations in customer handling ,preparation and application which are not known or under our control, LORCHEM cannot make any warranties related to the product or the performance of the product. Moreover, we underline the fact that in industrial applications, a tolerance of 5% in the overall results is considered normal and is not caused by the quality of the product.

CONTACT

PH: +1(450)424-4000
 F: +1(450) 424-9134
<http://www.lorchemintl.com>

LORCHEM INTERNATIONAL
 150,Rue Aimé-Vincent Vaudreuil, Dorion,
 QC J7V5V5