TECHNICAL DATA SHEET

AVERSA 90

SELF SEAL PRECAT TOPCOAT

DESCRIPTION

AVERSA 90 is a fast drying, self-seal precatalyzed lacquer for interior wood applications. AVERSA 90 Clear Precatalyzed Lacquer can be applied as a self-sealed system or over LORCHEM recommended sealers.

PRODUCT DATA

Color	Clear	**VOC actual**	639.91 g/L
Solids % by Vol		**VOC less exempts**	
Solids %by Wt	24% ± 2%	**Photochemical reactive**	No
Density	0.89		
Viscosity 23°C/73°F #4 Ford	18 ± 2	**Shelf life**	6 months (at 15-25°C/59-77°F)
Gloss(On Black glass @60°)	20, 35,50,90/Available in other gloss level	**Theo-coverage @1 mil dry**	232 Sq.Ft/gal 6 m^2/L

PREPARATION/APPLICATION

Working Temp	>18°C/65°F surface, coating and air
Catalyzation	N/A
Pot life	N/A
Reducer	Product can be applied without reduction. If reduction is needed to optimize application, reduce 15-25% by volume with DX 180 THINNER (Medium), DX 195 THINNER (slow). To help reduce trapped air, blushing or orange peel, use Retarder LR236 at a maximum of 5%.by volume.
Suggested Sealer	VS SEALER, MV 22 SANDING SEALER, MV 25 SANDING SEALER
Application	♦Color Wood-Stain or tone as desired and dry thoroughly ♦Seal- Apply a full coat of AVERSA 90 as a sealer or seal with a recommended sealer at 4.0 – 6.0 wet mils. ♦Allow to dry, sand with 240, 320 paper, or sponges as required. Topcoat within 8 hours of sanding ♦Topcoat – apply Aversa 90 at 4.0 - 6.0 mils wet ♦For more depth or build, sand and apply an additional coat.
Surface Preparation	Wood surface must be clean, dry, and finish sanded with 180 grit sandpaper Substrate should be clean and free of grease and oil to ensure optimum adhesion and coating performance properties. Moisture content of the wood should be between 6%-8%.
Use Directions	For interior use only. Adjust viscosity and stir thoroughly before application to avoid variations application. Dry time can be directly impacted by many factors, including film thickness. Users are urged to test the system under shop conditions.
App equip.	Conventional & HVLP Siphon Feed, Pressure Pot Systems and Airless/Air Assist Equipment.
Tinting	Can be tinted up to 15% maximum with universal colorants 844.
Cleanup	Clean tools/equipment immediately after use with T 750 LORCHEM cleaner gun or a quality lacquer thinner or acetone. Always follow manufacturer's safety recommendations when using any solvent.
Standards	This product meets KCMA and CKCA standards when used as a self-seal system or over recommended LORCHEM sealers.

DRYING TIMES

Method	Drying temperature.	Drying Time (@ 50%RH and thickness @ 4 mil WET)			
Air Drying	23°C/74°F	**Dust free time**	4-6 minutes	**Dry to sand**	1 hours
		Dry to touch	20-30 minutes	**Dry to recoat**	1 hour
		Dry to Handle	1 hour	**Dry to stack**	24 hours
Force dry	45 to 60°C/110-140°F	Minutes			

Note: Dry times are greatly affected by film build, porosity of substrate, air movement as well as heat and humidity. Minimum curing temperatures of 23°C/74°F must be maintained throughout curing cycle to achieve the film integrity as stated in product features.

AVERSA 90

SELF SEAL PRECAT TOPCOAT

APPLICATION RECOMMENDATIONS

APPLICATION EQUIPMENT SETTINGS

Method of Application	Air Pressure (PSI)	Fluid Pressure (PSI)	TIP size (mm / inch)	Application Viscosity (#FORD 4)	Thickness Film (Mils)
Conventional spray	40-50	08-12	1.8-2/0,070-0,078	18-21	3-5
Airless Spray	10-18	300-600	0,28-0,33/0,011-0,012	18-21	3-5
HVPL	35-45	8-12	1.19-1,39/0,047-0,055	18-21	3-5

Note: All measurements and application equipment settings are based on application at a temperature of 77°F. Viscosity will vary depending on the temperature of the liquid. The above-mentioned application equipment recommendations are guidelines only. The noted settings are starting point recommendations and that adjustment to the settings and equipment may be needed to obtain the desired results. Please refer to your specific equipment manufacturer's recommendations for equipment set-up.

SPECIFICATIONS

- For interior use only.
- Must be stirred before and during using.
- Store at room temperature (under25°C/ 80° F) after catalyzation. Higher temperatures will reduce the storage life.
- Self-seal or apply over recommended LORCHEM sealer. Please contact your LORCHEM representative for system recommendations.
- Total film thickness of systems must not exceed 7.0 mils dry film because heavier films may show cracking tendency.
- AVERSA 90 will yellow over time. With wood tone stains, this yellowing makes a warmer, softer appearance. Where white stains, pickled finishes, or white basecoats are used, nitrocellulose lacquer should not be used because of the yellowing of the sealer and topcoat may be considered objectionable. For these applications, LORCHEM Acrylic Conversion Coating (POLYACRIL 99) is recommended.

CAUTIONS

TESTING

Due to the wide variety of substrates, surface preparation methods, application methods, and environments, the customer should test the complete system for adhesion, compatibility and performance prior to full scale application.

THESE PRODUCT ARE DESIGNED FOR INDUSTRIAL SHOP APPLICATION AND PROFESSIONAL USE ONLY

Thoroughly review Safety Data Sheet (SDS) for safety information and cautions prior to using this product. Please direct any questions or comments to your local representative.

PDS

Product Data Sheets are periodically updated to reflect new information relating to the product. It is important that the customer obtain the most recent Product Data Sheet for the product being used. The information, rating, and opinions stated here pertain to the material currently offered and represent the results of tests believed to be reliable. However, due to variations in customer handling ,preparation and application which are not known or under our control, LORCHEM cannot make any warranties related to the product or the performance of the product. Moreover, we underline the fact that in industrial applications, a tolerance of 5% in the overall results is considered normal and is not caused by the quality of the product.

CONTACT

PH: +1(450)424-4000
F: +1(450) 424-9134
http://www.lorchemintl.com

LORCHEM INTERNATIONAL
150,Rue Aimé-Vincent Vaudreuil, Dorion,
QC J7V5V5